

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371**

ATTORNEY'S DOCKET NUMBER

0649-0800P

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

09/913332

INTERNATIONAL APPLICATION NO.

PCT/JP00/01742

INTERNATIONAL FILING DATE

March 22, 2000

PRIORITY DATE CLAIMED

December 21, 1999

TITLE OF INVENTION

THERMOPLASTIC RESIN COMPOSITION

APPLICANT(S) FOR DO/EO/US

SUZUKI, Katsumi; HOSHINA, Toshikazu

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND**-or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39 (1).
4. ☐ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau. WO 01/46316
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is transmitted herewith.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4)
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☒ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 20. below concern document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98-International Search Report (PCT/ISA/210) w/ 5 documents
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A FIRST preliminary amendment.
14. ☐ A SECOND or SUBSEQUENT preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821-1.825.
18. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☒ Other items or information:
1.) Two (2) sheets of Formal Drawings

U.S. APPLICATION NO. (optional, see 37 CFR 1.5) <div style="font-size: 1.5em; font-weight: bold; margin-top: 10px;">3332</div>	INTERNATIONAL APPLICATION NO. PCT/JP00/01742	ATTORNEY'S DOCKET NUMBER 0649-0800P
---	---	--

21. ☒ The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)):
 Neither international preliminary examination fee (37 CFR 1.482)
 nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO
 and International Search Report not prepared by the EPO or JPO. **\$1,000.00**

International preliminary examination fee (37 CFR 1.482) not paid to
 USPTO but International Search Report prepared by the EPO or JPO **\$860.00**

International preliminary examination fee (37 CFR 1.482) not paid to USPTO
 but international search fee (37 CFR 1.445(a)(2)) paid to USPTO. **\$710.00**

International preliminary examination fee (37 CFR 1.482) paid to USPTO
 but all claims did not satisfy provisions of PCT Article 33(1)-(4) **\$690.00**

International preliminary examination fee (37 CFR 1.482) paid to USPTO
 and all claims satisfied provisions of PCT Article 33(1)-(4). **\$100.00**

ENTER APPROPRIATE BASIC FEE AMOUNT =

Surcharge of **\$130.00** for furnishing the oath or declaration later than ☐ 20 ☐ 30
 months from the earliest claimed priority date (37 CFR 1.492(e)).

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	8 - 20 =	0	X \$18.00	\$	0
Independent Claims	1 - 3 =	0	X \$80.00	\$	0
MULTIPLE DEPENDENT CLAIM(S) (if applicable)	None		+ \$270.00	\$	0
TOTAL OF ABOVE CALCULATIONS =				\$	860.00

☐ Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.

SUBTOTAL = \$ 860.00

Processing fee of **\$130.00** for furnishing the English translation later than ☐ 20 ☐ 30
 months from the earliest claimed priority date (37 CFR 1.492(f)).

TOTAL NATIONAL FEE = \$ 860.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be
 accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). **\$40.00 per property** +

TOTAL FEES ENCLOSED = \$ 900.00

	Amount to be:	
	refunded	\$
	charged	\$

CALCULATIONS

PTO USE ONLY

a. ☒ A check in the amount of \$ **900.00** to cover the above fees is enclosed.

b. ☐ Please charge my Deposit Account No. _____ in the amount of \$ _____ to cover the above fees.
 A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 02-2448.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

Send all correspondence to:
Birch, Stewart, Kolasch & Birch, LLP or Customer No. 2292
 P.O. Box 747
 Falls Church, VA 22040-0747
 (703)205-8000

Date: August 13, 2001

By
 Raymond C. Stewart, #21,066

09/913332

1003 Rec'd PCT/PTO

13 AUG 2001

PATENT
0649-0800P

IN THE U.S. PATENT AND TRADEMARK OFFICE

Applicant: SUZUKI, Katsumi et al. Conf.:
Int'l. Appl. No.: PCT/JP00/01742
Appl. No.: New Group:
Filed: August 13, 2001 Examiner:
For: THERMOPLASTIC RESIN COMPOSTION

PRELIMINARY AMENDMENT

BOX PATENT APPLICATION

Assistant Commissioner for Patents
Washington, DC 20231

August 13, 2001

Sir:

The following Preliminary Amendments and Remarks are respectfully submitted in connection with the above-identified application.

AMENDMENTS

IN THE SPECIFICATION:

Please amend the specification as follows:

Before line 1, insert --This application is the national phase under 35 U.S.C. § 371 of PCT International Application No. PCT/JP00/01742 which has an International filing date of March 22, 2000, which designated the United States of America and was not published in English.

09/913332

JCS/RC/STW/TO 13 AUG 2001

Docket No. 0649-0800P

REMARKS

The specification has been amended to provide a cross-reference to the previously filed International Application.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. § 1.16 or under 37 C.F.R. § 1.17; particularly, extension of time fees.

Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By


Raymond C. Stewart, #21,066

P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

RCS/cqc
0649-0800P

(Rev. 02/12/01)

21 pgs

09/913332

JCO3 Rec'd PATENTD 13 AUG 2001

DESCRIPTION

THERMOPLASTIC RESIN COMPOSITION

TECHNICAL FIELD

The present invention relates to a thermoplastic resin composition rich in heat resistance and oil resistance and excellent in tensile elongation properties.

BACKGROUND ART

Styrene resins are used widely as an injection molding material or sheet forming material because of its rigidity, good stability and low cost. They however have stress cracks under the influence of a fatty oil or organic solvent and undergo a drastic deterioration in physical properties. In addition, since they are amorphous and have a glass transition point of about 90°C, they easily change in shape at a relatively low temperature not greater than 90°C. These drawbacks prevent free use of them.

There has accordingly been an attempt to prepare a resin composition having improved oil resistance and chemical resistance by adding, to a styrene resin, a propylene resin having excellent oil resistance.

09/913332

Proposed in JP-A-54-53159 (The term "JP-A" as used herein means an "unexamined published Japanese patent application") and JP-A-54-13354 are compositions obtained by adding a compatibilizer to a composition of a styrene resin and a propylene resin, which have inherently difficulty in mixing, in order to improve their compatibility. For example, in JP-A-54-53159, proposed is a thermoplastic composition obtained from a polystyrene resin and a polyethylene or poly- α -olefin resin by using, as a compatibilizer, a selectively hydrogenated linear, sequential or radial teleblock copolymer which comprises a polymerized aromatic vinyl compound A and an olefin elastomer B and has a structure of A-B-A, A-(B-A-B)_n-A, A(BA)_nB, B(A)₄ or B[(AB)_nB]₄ (wherein, n stands for an integer of 1 to 10). In the block copolymer serving as a compatibilizer, a block of the polymerized aromatic vinyl compound preferably accounts for 15 to 40 wt.% of all the block polymers, the olefin elastomer B is preferably a hydrogenated saturated polybutadiene, and 30 to 50% of butadiene carbon atoms are vinyl side chains. As its specific example, an SEBS block copolymer having a 30 wt.% of a bound styrene content is disclosed. However, owing to a low content of the aromatic vinyl compound block, this block copolymer lacks affinity with a styrene resin. An amount of the

block copolymer which can exist on the interface as a compatibilizer for the styrene resin and propylene resin is not sufficient so that the resulting composition is poor in tensile elongation properties. In JP-A-56-38338, on the other hand, proposed is a thermoplastic resin composition formed of a polyolefin resin and a polystyrene resin by using, as a compatibilizer, a hydrogenated block copolymer available by hydrogenating a block copolymer having at least one aromatic vinyl compound polymer block A and at least one conjugated diene polymer block B and containing 15 to 85 wt.% of a bound vinyl-substituted aromatic compound, thereby saturating at least 70% of double bonds in the block copolymer. In Examples, disclosed as a compatibilizer for a composition of a styrene resin and a propylene resin is A-B-A-B tapered 4 type hydrogenated block copolymers having a bound styrene content of 40 wt.% and a vinyl content, before hydrogenation, of 13%. These hydrogenated block copolymers involve drawbacks such as complex structure and cumbersome preparation process. There is accordingly a demand for a hydrogenated block copolymer which has a simple structure and can be prepared easily. In JP-A-5-186660 and JP-A-6-184366, proposed are resin compositions having excellent heat resistance, chemical resistance and oil resistance and

formed from a rubber-modified styrene resin and a polyolefin resin by using, as a compatibilizer, a hydrogenated triblock copolymer which comprises a styrene block, isoprene block, and a styrene block, with these styrene blocks accounting for 40 to 70 wt.% of these blocks. The hydrogenated triblock copolymer having an isoprene block is however inferior in weather resistance and heat resistance and has a problem in recycling properties. In addition, these resin compositions are not always satisfactory in tensile elongation properties, because adhesion of the styrene resin phase and propylene resin phase on the interface therebetween is insufficient.

An object of the invention is to provide a thermoplastic resin composition rich in heat resistance and oil resistance and having excellent tensile elongation properties by adding, to a styrene resin and a propylene resin, a hydrogenated block copolymer having a specific structure.

DISCLOSURE OF THE INVENTION

The object of the invention has been achieved by a thermoplastic resin composition comprising (A) a styrene resin, (B) a propylene resin and (C) a hydrogenated block copolymer comprising at least two polystyrene blocks Xs

and at least one polybutadiene block Y, with at least 70 % of the double bonds of the polybutadiene of the polybutadiene block Y having been hydrogenated, wherein a styrene content of the hydrogenated block copolymer (C) is 40 to 80 wt.%, a 1,2-bound content of the polybutadiene block is 30 to 80 wt.%, a weight ratio of the component (A) to the component (B) is 95:5 to 5:95, a content of the component (C) is 2 to 30 parts by weight based on 100 parts by weight of the components (A) and (B), and at least 50% of the component (C) exists on the interface between the phase of the component (A) and the phase of the component (B).

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a phase separation structure of a thermoplastic resin composition of Example 1 of the invention observed through a transmission electron microscope; and FIG. 2 illustrates a phase separation structure of a thermoplastic resin composition of Comparative Example 2 observed through a transmission electron microscope.

BEST MODE FOR CARRYING OUT THE INVENTION

In the invention, examples of the styrene resin (A) include homopolymers or copolymers obtained using, as a

monomer component, styrene, methylstyrene, ethylstyrene, isopropylstyrene, dimethylstyrene, paramethylstyrene, chlorostyrene, bromostyrene, vinyltoluene or vinylxylene, styrene-maleic anhydride copolymer, styrene-acrylic acid copolymer, styrene-acrylate copolymer, styrene-methacrylic acid copolymer, styrene-acrylonitrile copolymer and acrylonitrile-butadiene-styrene copolymer. In addition, an impact-resistant polystyrene resin obtained by mixing the above-described polystyrene resin with at least one of a butadiene rubber, ethylene-propylene rubber and a styrene butadiene rubber or graft polymerizing the latter on the former can also be used. The styrene resin of the invention has preferably a melt index (MI: at 200°C under a load of 5 Kg) of 0.5 to 20 g/10 min, more preferably 1 to 10 g/10 min.

In the invention, no particular limitation is imposed on the propylene resin (B) insofar as it is a polymer obtained by polymerizing a propylene monomer as a main component. A propylene resin obtained by copolymerizing with up to about 20 wt.% of another α -olefin such as ethylene, butene or 4-methylpentene-1 may be used. Either a random copolymer or block copolymer may be used. Moreover, a propylene resin may contain up to about 40 wt.% of an olefin thermoplastic elastomer such as a copolymer rubber with at least 2 α -olefins

selected from ethylene, propylene, 1-butene, 1-hexene, 4-methyl-pentene and 1-octene or a copolymer rubber comprising an α -olefin and various monomers. Typical examples of the copolymer rubber with the at least 2 α -olefins include ethylene-propylene copolymer rubber (EPR), ethylene-butene copolymer rubber (EBR) and ethylene-propylene-diene copolymer rubber (EPDM). In the invention, preferred as the propylene resin (B) is a syndiotactic polypropylene homopolymer or a propylene-ethylene block resin having a crystal-melting peak temperature by DSC of 155°C or greater. Use of it heightens the heat deformation temperature of the resulting composition.

The propylene resin of the invention has preferably a melt flow rate (MFR, at 230°C under a load of 2.16 Kg) of 0.5 to 60 g/10 min, more preferably 1 to 20 g/10 min. Melt flow rates less than 0.5 g/10 min deteriorate the moldability or formability of the resulting thermoplastic resin composition, while melt flow rates exceeding 60 g/min deteriorate impact resistance. Melt flow rates outside the above-described range are therefore not preferred.

In the invention, the hydrogenated block copolymer (C) comprises at least two polystyrene blocks Xs and at least one polybutadiene block Y, and has at least 70% of

the double bonds of the polybutadiene of the polybutadiene block Y has been hydrogenated. The polystyrene block X may be a styrene homoblock or a block comprising styrene as a main component and 40 wt.% or less of another aromatic vinyl compound copolymerizable with styrene. Examples of the another aromatic vinyl compound include α -methylstyrene, 4-methylstyrene, 1,1-diphenylethylene and divinylbenzene. The polybutadiene block Y may be a butadiene homoblock or a block comprising butadiene as a main component and a 40 wt.% or less of another conjugated diene compound or aromatic vinyl compound copolymerizable with butadiene. Examples of the another conjugated diene compound copolymerizable with butadiene include isoprene, 2,3-dimethyl-1,3-butadiene, 1,3-pentadiene, 2-methyl-1,3-butadiene, 1,3-hexadiene, 4,5-diethyl-1,3-octadiene, 3-butyl-1,3-octadiene, myrcene and ocimene, while those of the aromatic vinyl compound include styrene, α -methylstyrene, 4-methylstyrene, 1,1-diphenylethylene and divinylbenzene.

The styrene content of the hydrogenated block copolymer (C) is 40 to 80 wt.%, preferably 45 to 80 wt.%. When the styrene content is less than 40 wt.%, the hydrogenated block copolymer (C) and the styrene resin lack affinity therebetween and the amount of the hydrogenated block copolymer existing on the interface

between the styrene resin phase and the propylene resin phase becomes insufficient, resulting in unsatisfactory compatibilizing effects. When the styrene content exceeds 80 wt.%, on the other hand, the affinity with the styrene resin phase becomes excessive and the hydrogenated block copolymer is inevitably incorporated in the styrene resin phase, resulting also in unsatisfactory compatibilizing effects. When the hydrogenated block copolymer (C) contains another aromatic vinyl compound in addition to styrene, the styrene content means wt.% of all the aromatic vinyl compounds.

The 1,2-bound content of the butadiene unit of the polybutadiene block Y of the hydrogenated block copolymer (C) is 30 to 80 wt.%, preferably 40 to 80 wt.%. When the 1,2-bound content is less than 30 wt.%, the polybutadiene block and propylene resin after hydrogenation lack affinity therebetween, preventing the hydrogenated block copolymer from bringing about sufficient compatibilizing effects. When it exceeds 80 wt.%, on the other hand, the affinity with the propylene resin becomes excessive and the hydrogenated block copolymer is inevitably incorporated in the propylene resin phase, resulting in insufficient compatibilizing effects.

In the hydrogenated block copolymer (C), at least 70% of the double bonds of the polybutadiene of the polybutadiene block have been hydrogenated. Hydrogenation ratios less than 70% tend to lower elongation properties and heat resistance of the resulting composition.

It is preferred that the polystyrene block X of the hydrogenated block copolymer (C) has a weight-average molecular weight of 5000 to 50000, while the polybutadiene block Y has a weight-average molecular weight of 5000 to 70000. Weight-average molecular weights of the polystyrene block X not greater than 5000 lower the affinity with the styrene resin of the polystyrene block X, while weight-average molecular weights of the polybutadiene block Y not greater than 5000 lower the affinity with the propylene resin of the hydrogenated polybutadiene block Y, leading to inferior compatibilizing effects. When the weight-average molecular weight of the polystyrene block X is 50000 or greater or the weight-average molecular weight of the polybutadiene block Y is 70000 or greater, on the other hand, the molecular weight which becomes too large as the hydrogenated block copolymer causes an rise in the melt viscosity. Then, dispersion in the resin composition comprising a styrene resin and a propylene resin becomes

insufficient, resulting in inferior compatibilizing effects.

The hydrogenated block copolymer (C) has preferably a melt flow rate (MFR, at 230°C under a load of 2.16 Kg) of 0.1 to 50 g/10 min, more preferably 0.5 to 20 g/10 min, still more preferably 1 to 10 g/10 min. At a melt flow rate less than 0.1 g/10 min, the melt viscosity becomes too high, which makes it impossible to obtain sufficient compatibilizing effects. Melt flow rates exceeding 50 g/min, on the other hand, make it impossible to obtain reinforcing effects on the interface between the styrene resin and propylene resin.

In the invention, it is necessary that at least 50%, more preferably at least 60%, of the hydrogenated block copolymer (C) exists on the interface between the styrene resin (A) and the propylene resin (B). At an existing ratio less than 50%, even if the styrene resin and propylene resin form a mutually-impregnation phase separation structure, the resulting composition does not exhibit excellent tensile elongation properties because of inferior adhesion strength on their interface.

In the invention, the styrene resin (A) and propylene resin (B) are mixed at a weight ratio of 95:5 to 5:95. It is possible to adjust this composition ratio, for example, to increase the ratio of the styrene

resin (A) when heightening of rigidity is intended, or to increase the ratio of the propylene resin when heat resistance and oil resistance are important. From the viewpoint of the balance between rigidity and heat resistance or oil resistance, a preferred weight ratio of the styrene resin (A) to the propylene resin (B) is 80:20 to 40:60.

The amount of the hydrogenated block copolymer (C) is 2 to 30 parts by weight, preferably 5 to 15 parts by weight, based on 100 parts by weight of the styrene resin (A) and propylene resin (B). Amounts less than 2 parts by weight cannot bring about sufficient compatibilizing effects. Amounts exceeding 30 parts by weight lower rigidity and in addition, are not economical.

In the invention, as the hydrogenated block copolymer (c), a triblock copolymer having an X-Y-X structure is preferably employed. In this case, the styrene content of the hydrogenated block copolymer (C) preferably exceeds 50 wt.% but not greater than 80 wt.%. The 1,2-bound content of the polybutadiene block Y of the hydrogenated block copolymer (C) is preferably 45 to 75 wt.%, more preferably 55 to 70 wt.%.

As one of preferred modes in the invention, the hydrogenated block copolymer (C) has an Y-X-Y-X or Y-X-Y-X-Y structure. In this case, the styrene content of the

hydrogenated block copolymer (C) preferably exceeds 50 wt.% but not greater than 80 wt.%. The 1,2-bound content of the polybutadiene block Y of the hydrogenated block copolymer (C) is preferably 30 wt.% or greater but less than 60 wt.%.

No particular limitation is imposed on the preparation process of the hydrogenated block copolymer (C) and a known process is adopted. For example, a block copolymer comprising a polystyrene block X and a polybutadiene block Y can be prepared in an inert solvent by using a technique of living anionic polymerization in the presence of an organic lithium catalyst, which technique has been described in JP-B-36-19286. Described specifically, it can be prepared, for example, by successively forming blocks in the order of X, Y and X in the presence of, as an organolithium catalyst, a monolithium compound such as n-butyl lithium, sec-butyl lithium or tert-butyl lithium, by forming an X-Y two-type living block copolymer in the order of X and Y and then forming a triblock copolymer of an X-Y-X structure by using a bifunctional coupling agent, or by forming a triblock copolymer of an X-Y-X structure in the order of Y and X by using a dilithium compound.

The styrene content of the hydrogenated block copolymer (C) of the invention is adjusted by a feed

monomer composition of styrene and butadiene. Upon polymerization, a polar compound or randomizing agent can be used for the purpose of adjusting a polymerization rate or changing the microstructure (cis, trans or 1,2-bound ratio) of the polymerized butadiene block.

Examples of the polar solvent or randomizing agent include amines such as N,N,N',N'-tetramethylethylenediamine, trimethylamine, triethylamine and diazobicyclo[2,2,2]octane, ethers such as tetrahydrofuran, diethylene glycol dimethyl ether and diethylene glycol dibutyl ether, thioethers, phosphines, phosphoramides, alkylbenzene sulfonates and alkoxides of potassium or sodium.

A hydrogenated block copolymer with at least 70% of the double bonds of the butadiene block having been selectively hydrogenated can be obtained by subjecting a solution of the block copolymer obtained above in a hydrocarbon solvent or a solution obtained by dissolving the block copolymer in a hydrocarbon solvent to hydrogenation reaction (which will hereinafter be called "hydrogenation"). The hydrogenation of the block copolymer solution may be conducted while the terminal is active or after inactivating the active terminal by a polymerization terminator.

As the catalyst to be used for hydrogenation, known are (1) a supported-type heterogeneous catalyst system and (2) a homogeneous catalyst using a Ziegler catalyst or a titanocene compound. In accordance with a process as described in JP-B-42-8704 or JP-B-43-6636, preferably a process as described in JP-B-63-441 or JP-B-63-5401, hydrogenation is conducted in the presence of a hydrogenation catalyst in an inert solvent, whereby a solution of a hydrogenated block copolymer is available.

By removing the solvent from the solution of a hydrogenated block copolymer thus obtained in a conventional manner, the hydrogenated block copolymer can be obtained. A step for deashing a metal can be adopted if necessary. A reaction terminator, antioxidant, neutralizing agent or surfactant may be used as needed.

To the thermoplastic resin composition of the invention, any additive can be added as needed. No particular limitation is imposed on the nature of the additive insofar as it is ordinarily employed for reparation of a resin. Examples include inorganic fillers such as silica, calcium carbonate, magnesium carbonate, calcium sulfate and talc, organic fibers, pigments such as titanium oxide, carbon black and iron oxide, lubricants or mold releasing agents such as stearic acid, behenic acid, zinc stearate, calcium

stearate, magnesium stearate and styrene-bis-stearamide, plasticizers such as organopolysiloxane and mineral oils, antioxidants such as hindered phenol and phosphor antioxidants, flame retardants, ultraviolet absorbers, antistatic agents, and reinforcing agents such as glass fibers, carbon fibers and metal whisker; the other additives; and mixtures thereof.

No particular limitation is imposed on the preparation method of the resin composition of the invention insofar as it permits existence of at least 50% of the hydrogenated block copolymer (C) on the interface between the styrene resin (A) phase and propylene resin (B) phase. A known method can be utilized. Examples include a method of kneading components under a molten state in an ordinarily employed mixer such as Banbury mixer, single screw extruder, twin screw extruder, co-kneader or a multi screw extruder: or a method of dissolving or dispersing components in a solvent and then removing the solvent by heating. Preferred is a method of kneading under conditions permitting a shear rate of at least 100 sec^{-1} at 180°C or greater, preferably 200°C or greater, under which the styrene resin (A) phase, propylene resin (B) phase and the hydrogenated block copolymer (C) can be mixed and melted sufficiently and the hydrogenated block copolymer (C) moves to the

interface between the styrene resin (A) phase and the propylene resin (B) phase. Use of a twin screw extruder is preferred. The components are preferably kneaded once by the above-described method to form master pellets, followed by molding or forming and, if necessary, expansion molding.

Next, Examples in order to illustrate the present invention in greater detail are shown below, but the invention should not be construed as being limited thereto. The values shown in these Examples were measured by the methods described below. In Examples, the "part" and "%" is in terms of weight unless otherwise particularly indicated. Measurements in Examples were conducted in accordance with the following methods.

(1) Styrene content: measured by infrared spectroscopy based on the absorption of a phenyl group at 679 cm^{-1} .

(2) 1,2-Bound content of the polybutadiene block: by measured by infrared spectroscopy and calculated from Hampton method.

(3) Hydrogenation ratio: calculated from 100-MHz ^1H -NMR spectrum by using ethylene tetrachloride as a solvent.

(4) Weight-average molecular weight: measured using gel permeation chromatography (GPC) at 40°C in a THF solvent.

(5) Tensile elongation properties: A tensile elongation at break of injection-molded test piece of a resin composition was measured in accordance with ASTM D638 and it was used as an index.

(6) Rigidity: Flexural modulus of an injection molded test piece of a resin composition was measured by a three-point bending test in accordance with ASTM D790 and it was used as an index.

(7) Heat resistance: A vicat softening point of an injection molded test piece of a resin composition was measured under a load of 1 kgf in accordance with ASTM D5125 and it was used as an index.

(8) Oil resistance: A resin composition was formed into a sheet of 1 mm thick by a sheet extruder. By using the sheet, a container of 2 cm in height x 10 cm in length x 10 cm in width was formed. After application of a synthetic coconut oil to the inside surface of the container, it was heated in an oven for 1 hour. A heating temperature at which a changing ratio of the internal volume of the container by the above-described heating became 10% or greater was used as an index.

(8) Phase separation structure: From an injection molded piece of a resin composition, an ultra-thin section was cut out along a face parallel with a flow direction, upon molding or forming, of the resin by an ultra-microtome and it was stained with ruthenium tetroxide. From the observation of the image at 25000x magnification under a transmission electron microscope, the phase separation structure of the styrene resin phase and propylene resin phase was observed.

(10) Existing ratio of block copolymer on the interface (a ratio of the hydrogenated block copolymer existing on the interface between the styrene resin phase and the propylene resin phase was measured and calculated based on the total amount of the hydrogenated block copolymer by the below-described method and it was used as an index): An image obtained by the above-described observation (9) of the phase separation structure under a transmission electron microscope was photographed. Based on the analysis of this photographed image, an area of the hydrogenated block copolymer existing in the styrene resin phase or propylene resin phase was measured and its ratio (a) to the whole area subjected to image analysis was calculated. Supposing that a weight ratio of the hydrogenated block copolymer calculated from the mixing ratio of the resin composition was (b), a ratio (c) of

the hydrogenated block copolymer existing on the interface between the styrene resin phase and propylene resin phase was $((b)-(a))/(b) \times 100\%$. This ratio was used as an index.

Examples 1 to 8 and Comparative Examples 1 to 4

At a temperature maintained at 50°C, an autoclave having a content volume of 5 liter and equipped with a stirrer and a jacket was fed with 250 g of styrene and 1250 g of cyclohexane which had been purified in advance. Polymerization was initiated by adding thereto 0.5 g, in terms of butyl lithium, of a hexane solution of butyl lithium. One hour after the addition of the catalyst, 250 g of butadiene and 1250 g of cyclohexane, which had been purified and dried in advance, were added and they were polymerized at 50°C. After one hour, 250 g of styrene and 1250 g of cyclohexane were added and polymerization was conducted for 1 hour. Upon polymerization, tetramethylethylene diamine was added to regulate the 1,2-bound content of the polybutadiene block moiety.

The resulting block copolymer solution was diluted with cyclohexane to a concentration of 5 wt.%. To the diluted block copolymer solution, 1.175 g, in terms of nickel, of a hexane solution of nickel octenoate and 6.85 g, in terms of triethyl aluminum, of a hexane solution of

triethyl aluminum were added as a catalyst. The resulting mixture was reacted at 50°C for about 6 hours under hydrogen pressure. The resulting hydrogenated block copolymer solution was washed three times with an aqueous hydrochloric acid solution. From the thus-washed hydrogenated copolymer solution, the hydrogenated copolymer was precipitated using excess methanol. The precipitate was dried under reduced pressure. The resulting hydrogenated block copolymer (I) was found to have a styrene content of 67%, a 1,2-bound content of the polybutadiene block of 41%, and a hydrogenation ratio of 97%.

In a similar manner, hydrogenated block copolymers (I) to (VII) having a structure as described in Table 1 were prepared.

Table 1

Structure of hydrogenated copolymer	I	II	III	IV	V	VI	VII
Block structure	X-Y-X	X-Y-X	X-Y-X	X-Y-X-Y	X-Y-X	X-Y-X	X-Y-X
Styrene content	67%	70%	50%	67%	35%	68%	67%
Molecular weight of polystyrene block X	15000	15000	16000	15000	10000	15400	15000
1,2-bound content of polybutadiene block Y	40%	65%	40%	40%	41%	20%	40%
Molecular weight of polybutadiene block Y	15000	13000	32000	75000	37000	14500	15000
Hydrogenation ratio of polybutadiene block Y	97%	98%	97%	97%	96%	96%	20%

Seven hydrogenated block copolymers thus obtained were each mixed with a commercially available impact-resistance styrene resin (HIPS, "SR500", product of Dainippon Ink & Chemicals, Inc.), styrene resin (GPPS, "G9305", product of A & M styrene Co., Ltd.) or acrylonitrile-butadiene-styrene resin (ABS, "A4130", product of Asahi Kasei Corporation) and a block propylene resin (b-PP, "K7019", product of Chisso Corporation) at a ratio as shown in Table 2 or 3, followed by mixing for about 10 minutes in a super mixer. The resulting mixture was kneaded under a molten state at 210 to 230°C in a 30-mmØ twin screw extruder, whereby a composition was obtained in the form of pellets. These pellets were measured for various properties. Composition ratios and measuring results are shown in Tables 2 and 3.

Table 2

	Ex. 1	Ex. 2	Ex. 3	Ex. 4	Ex. 5	Ex. 6	Ex. 7	Ex. 8
Structure of hydrogenated block copolymer	I	I	I	I	II	III	IV	I
Hydrogenated block copolymer (parts)	6	15	6	10	6	6	6	15
HIPS (wt.%)	70	70	50		70	70	70	
GPPS (wt.%)				70				
ABS (wt.%)								70
b-PP (wt.%)	30	30	50	30	30	30	30	30
Elongation at break (%)	120	180	300	100	240	100	130	100
Heat deformation temperature (°C)	107	107	112	107	109	106	107	105
Flexural modulus (kgf/cm ²)	17800	16400	15600	22000	17200	16600	17300	15400
Oil resistance (°C)	105	103	115	105	109	102	108	110
Phase separation structure	Mutual impregnation	Mutual impregnation	Mutual impregnation	Mutual impregnation	Mutual impregnation	Mutual impregnation	Mutual impregnation	Mutual impregnation
Existing ratio (%) of block copolymer on interface	85	70	95	83	90	70	87	67

Table 3

	Comp. Ex. 1	Comp. Ex. 2	Comp. Ex. 3	Comp. Ex. 4
Structure of hydrogenated block copolymer	-	V	VI	VII
Hydrogenated block copolymer (parts)	0	6	6	6
HIPS (wt.%)	70	70	70	70
GPPS (wt.%)	30	30	30	30
ABS (wt.%)	3	15	30	21
b-PP (wt.%)	30	30	50	30
Elongation at break (%)	106	106	107	108
Heat deformation temperature (°C)	107	107	112	107
Flexural modulus (kgf/cm ²)	19000	15800	16500	14000
Oil resistance (°C)	70	81	86	83
Phase separation structure	sea-island	Mutual impregnation	Mutual impregnation	Mutual impregnation
Existing ratio (%) of block copolymer on interface	-	30	45	40

Phase separation structure of each of the thermoplastic resin compositions of Example 1 and

Comparative Example 2 observed under a transmission electron microscope are shown in FIGS. 1 and 2, respectively. In FIG. 2, a number of hydrogenated block copolymers are dispersed in the propylene resin phase (the unstained light phase), while hydrogenated block copolymers scarcely exist on the interface between the styrene resin phase (the stained dark phase) and the propylene resin phase.

Compositions obtained in Examples of the invention all exhibited satisfactory results in any item.

In Comparative Example 1 free of a hydrogenated block copolymer, tensile elongation properties are inferior and oil resistance is insufficient. In Comparative Example 2 wherein the styrene content in the hydrogenated block copolymer is too small, the hydrogenated block copolymer has excessive affinity with the propylene resin, increasing the existing ratio of the hydrogenated block copolymer in the propylene resin phase. This means that the amount of the hydrogenated block copolymer is not enough for reinforcing the adhesion on the interface between the styrene resin phase and propylene resin phase, resulting in inferior tensile elongation properties and oil resistance. In Comparative Example 3, since the 1,2-bound content of the polybutadiene block of the hydrogenated block copolymer

is too small, the affinity with the propylene resin lowers, leading to an increase in the existing ratio of the hydrogenated block copolymer in the styrene resin phase. This makes the adhesion on the interface insufficient, whereby tensile elongation properties and oil resistance become inferior. In Comparative Example 4, a hydrogenation ratio of the hydrogenated block copolymer becomes too small and affinity with the propylene resin lowers, so that the existing ratio of the hydrogenated block copolymer on the interface becomes insufficient, resulting in inferior tensile elongation properties and oil resistance.

INDUSTRIAL APPLICABILITY

The hydrogenated block copolymer (C) to be used in the invention exists on the interface between a styrene resin phase and a propylene resin phase and reinforces this interface, which makes it possible to provide a thermoplastic resin composition having excellent heat resistance and oil resistance and having incomparable tensile elongation properties.

CLAIMS

1. A thermoplastic resin composition comprising:

(A) a styrene resin;

(B) a propylene resin; and

(C) a hydrogenated block copolymer comprising at least two polystyrene blocks X and at least one polybutadiene block Y, with at least 70 % of the double bonds of the polybutadiene of the polybutadiene block Y having been hydrogenated,

wherein the hydrogenated block copolymer (C) has a styrene content of 40 to 80 wt.%, a 1,2-bound content of the polybutadiene block Y is 30 to 80 wt.%, a weight ratio of the component (A) to the component (B) is 95:5 to 5:95, a content of the component (C) is 2 to 30 parts by weight based on 100 parts by weight of the components (A) and (B), and at least 50% of the component (C) exists at the interface between a phase of the component (A) and a phase of the component (B).

2. The thermoplastic resin composition according to claim 1, wherein in the component (C), the polystyrene block X has a molecular weight of 5000 to 50000, and the polybutadiene block Y has a molecular weight of 5000 to 70000.

3. The thermoplastic resin composition according to claim 1, wherein a weight ratio of the component (A) to the component (B) is 80:20 to 40:60.

4. The thermoplastic resin composition according to claim 2, wherein a weight ratio of the component (A) to the component (B) is 80:20 to 40:60.

5. The thermoplastic resin composition according to claim 1, wherein the component (C) is a triblock copolymer having an X-Y-X structure.

6. The thermoplastic resin composition according to claim 5, wherein the styrene content of the component (C) is exceeding 50 wt.% but not greater than 80 wt.%.

7. The thermoplastic resin composition according to claim 1, wherein the component (C) is a block copolymer having an X-Y-X-Y structure or Y-X-Y-X-Y structure.

8. The thermoplastic resin composition according to claim 7, wherein the 1,2-bound content of the polybutadiene block Y of the component (C) is at least 30 wt.% but less than 60 wt.%, and the styrene content of

the component (C) is exceeding 50 wt.% but not greater than 80 wt.%.

091332.081301


ABSTRACT

Provided is a thermoplastic resin composition comprising (A) a styrene resin, (B) a propylene resin and (C) a hydrogenated block copolymer comprising at least two polystyrene blocks Xs and at least one polybutadiene block Y, with at least 70 wt.% of the double bonds of the polybutadiene of the polybutadiene block Y having been hydrogenated, wherein the hydrogenated block copolymer (C) has a styrene content of 40 to 80 wt.%; a 1,2-bound amount of the polybutadiene block Y is 30 to 80 wt.%; a weight ratio of the component (A) to the component (B) is 95:5 to 5:95; the component (C) is contained in an amount of 2 to 30 parts by weight based on 100 parts by weight of the components (A) and (B); and at least 50% of the component (C) exists at the interface between a phase of the component (A) and a phase of the component (B). Existence of this component (C) makes it possible to yield a thermoplastic resin composition having excellent heat resistance and oil resistance and having comparable tensile elongation properties.

09/913332


1/2

Fig. 1



09913332.081301

Fig. 2



09/913332.081301

BIRCH, STEWART, KOLASCH & BIRCH, LLP

PLEASE NOTE:
YOU MUST
COMPLETE THE
FOLLOWING:

COMBINED DECLARATION AND POWER OF ATTORNEY FOR PATENT AND DESIGN APPLICATIONS

ATTORNEY DOCKET NO.
0649-0800P

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated next to my name; that I verily believe that I am the original, first and sole inventor (if only one inventor is named below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Insert Title:

THERMOPLASTIC RESIN COMPOSITION

Fill in Appropriate
Information -
For Use Without
Specification
Attached:

the specification of which is attached hereto. If not attached hereto,
the specification was filed on _____ as
United States Application Number _____; and /or
the specification was filed on March 22, 2000 as PCT
International Application Number PCT/JP00/01742; and was
amended under PCT Article 19 on _____ (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I do not know and do not believe the same was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months (six months for designs) prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as follows.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 (a)-(d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Insert Priority
Information:
(if appropriate)

➔ Prior Foreign Application(s)

P. Hei-11-362413

(Number)

Japan

(Country)

December/21/1999

(Month/Day/Year Filed)

Priority Claimed

☒

Yes

☐

No

(Number)

(Country)

(Month/Day/Year Filed)

☐

Yes

☐

No

(Number)

(Country)

(Month/Day/Year Filed)

☐

Yes

☐

No

(Number)

(Country)

(Month/Day/Year Filed)

☐

Yes

☐

No

(Number)

(Country)

(Month/Day/Year Filed)

☐

Yes

☐

No

Insert Provisional
Application(s):
(if any)

(Application Number)

(Filing Date)

(Application Number)

(Filing Date)

All Foreign Applications, if any, for any Patent or Inventor's Certificate Filed More Than 12 Months (6 Months for Designs) Prior To The Filing Date of This Application:

Country

Application No.

Date of Filing (Month/Day/Year)

Insert Requested
Information:
(if appropriate)

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

Insert Prior U.S.
Application(s):
(if any)

(Application Number)

(Filing Date)

(Status - patented, pending, abandoned)

(Application Number)

(Filing Date)

(Status - patented, pending, abandoned)

I hereby appoint the following attorneys to prosecute this application and/or an international application based on this application and to transact all business in the Patent and Trademark Office connected therewith and, in connection with the resulting patent based on instructions received from the entity who first sent the application papers to the attorneys identified below, unless the inventor(s) or assignee provides said attorneys with a written notice to the contrary: **Atty Dckt No.: 0649-0800P**

Terrell C. Birch	(Reg. No. 19,382)	Raymond C. Stewart	(Reg. No. 21,066)
Joseph A. Kolasch	(Reg. No. 22,463)	James M. Slattery	(Reg. No. 28,380)
Bernard L. Sweeney	(Reg. No. 24,448)	Michael K. Mitter	(Reg. No. 29,680)
Charles Gorenstein	(Reg. No. 29,271)	Gerald M. Murphy, Jr.	(Reg. No. 28,977)
Leonard R. Svensson	(Reg. No. 30,330)	Terry L. Clark	(Reg. No. 32,644)
Andrew D. Meikle	(Reg. No. 32,868)	Marc S. Weiner	(Reg. No. 32,181)
Joe McKinney Muncy	(Reg. No. 32,334)	Andrew F. Reish	(Reg. No. 33,443)
C. Joseph Faraci	(Reg. No. 32,350)	Donald J. Daley	(Reg. No. 34,313)

Send Correspondence to:

BIRCH, STEWART, KOLASCH & BIRCH, LLP

P.O. Box 747 • Falls Church, Virginia 22040-0747

Telephone: (703) 205-8000 • Facsimile: (703) 205-8050

PLEASE NOTE:
YOU MUST
COMPLETE THE
FOLLOWING:

Customer No. **062292**

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full Name of First or Sole
Inventor: 1 - 00

Insert Name of Inventor

Insert Date This

Document is Signed

Insert Residence

Insert Citizenship

Insert Post Office

Address

Full Name of Second

Inventor, if any: 2 - 00

see above

Full Name of Third

Inventor, if any

see above

Full Name of Fourth

Inventor, if any

see above

Full Name of Fifth


Inventor, if any

see above

GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
<u>Katsumi</u>	<u>SUZUKI</u>	<u>Katsumi Suzuki</u>	August 3, 2001
Residence (City, State & Country)		CITIZENSHIP	
<u>Kanagawa, Japan JPX</u>		<u>Japan</u>	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
<u>37-7, Kamikodanaka 1-chome, Nakahara-ku, Kawasaki-shi, Kanagawa 211-0053 Japan</u>			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
<u>Toshikazu</u>	<u>HOSHINA</u>	<u>Toshikazu Hoshina</u>	August 3, 2001
Residence (City, State & Country)		CITIZENSHIP	
<u>Kanagawa, Japan JPX</u>		<u>Japan</u>	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
<u>504, 2156, Kamikuratacho, Totsuka-ku, Yokohama-shi, Kanagawa 244-0816 Japan</u>			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			

* DATE OF SIGNATURE

United States Patent & Trademark Office
Office of Initial Patent Examination – Scanning Division



Application deficiencies found during scanning:

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☒ **Scanned copy is best available.** Drawings are very dark
Figures - 2.